

QEMETICA®	SALES SPECIFICATION	Effective date:	Juli 29, 2026
PRODUCT NAME	Agilon® 400G-D	Page	1 / 1

I. PARAMETERS

PARAMETER	SPECIFICATIONS		METHOD
	MIN	MAX	
Surface Area, BET-5, m ² /g	55	95	CD-25-15G
Moisture, as packaged, Wt %	3.5	7.5	CD-25-8D
pH	5.7	7.3	CD-25-9
Water Soluble Salts, Wt%	-	2.0	CD-25-23A
SH, Wt %	0.4	0.6	CD-25-60
Carbon, Wt %	3.0	5.0	CD-25-56

II. ADDITIONAL INFORMATION

Amorphous Precipitated Silica
 Appearance: essentially white, odorless pellets
 This specification is subject to change without notice.

III. STORAGE

Correct handling and storage are critical to maintaining product performance. Silica is hygroscopic, meaning it can absorb moisture over time even under optimal conditions. Qemetica recommends storing silica products in a dry, clean environment and ensuring they are protected from contact with other substances.

IV. REGULATORY INFORMATION

For specific inquiries, please contact your Qemetica sales or customer service representative.

Agilon® Performance Silica is registered trademarks of QEMETICA US Silica, LLC and QEMETICA NL Silica B.V.

**WE
CHEM DO
BETTER**

QEMETICA US Silica LLC

Westlake Division
 3150 Pete Manena Road
 P.O. BOX 1270
 Westlake, LA 70669
www.qemetica.com

Barberton Division
 900 Columbia Court
 Barberton, Ohio 44203

**Monroeville Business &
Technology Center**
 440 College Park Drive
 Monroeville, PA 15146

QEMETICA NL Silica B.V.

Delfzijl Division
 Valgenweg 1-3
 9936 HV Delfzijl, The Netherlands