

CARBOMIX® 1606K

CARBOMIX®1606K is a general purpose SBR oil/black masterbatch based on a cold polymerized polymer. This low Mooney version of CARBOMIX® 1606R is designed for operations requiring optimum processability, such as open mill mixing. CARBOMIX®1606K can be used in tires, tread rubber, and molded and extruded mechanical goods.

Notice: All information supplied by or on behalf of Lion Copolymer in relation to its products, whether in the nature of data, recommendations or otherwise, is supported by research and believed reliable, but Lion Copolymer assumes no liability whatsoever in respect of application, processing or use made of the aforementioned information or products, or any consequence thereof. The buyer undertakes all liability in respect of the application, processing or use of the aforementioned information or product, whose quality and other properties he shall verify, or any consequence thereof. No liability whatsoever shall attach to Lion Copolymer for any infringement of the rights owned or controlled by a third party in intellectual, industrial or other property by reason of the application, processing or use of the aforementioned information or products by the buyer.

PRODUCT DATA

Description

23.5% Bound Styrene SBR	100.0 parts
N330 Carbon Black(HAF)	52.0 parts
Highly Aromatic Oil	10.0 parts
Stabilizer	Staining
Emulsifier	Rosin Acid
Coagulant	Acid
Specific Gravity	1.13

Specifications

Volatile content, % max.	0.50
Organic Acid content, %	3.75 ± 1.00
Oil Content, %	6.15 ± 0.65
Carbon Black Content, %	31.95 ± 1.75
Unmilled Viscosity	50 ± 10

Rheometer Properties

ML, in-lbs.	1.6 ± 1.0
MH, in-lbs.	15.3 ± 2.0
ts1, minutes	3.8 ± 1.2
t'90, minutes	12.6 ± 2.5

Stress Strain Properties, PSI

Tensile	2800 min.
300% Modulus	1430 ± 300
Elongation%	480 min

Standard Test Formula

CARBOMIX®1606K	162.00
Zinc Oxide	3.00
Stearic Acid	1.50
TBBS	1.25
Sulfur	1.75

Test Methods

Volatiles	ASTM D5668	
Acid/Oil	ASTM D5774	
Unmilled Mooney Viscosity	ASTM D1646	UMS1+4@100° C
Rheometer Properties	ASTM D5289	100cpm, 0.5 degree arc, 160° C, 0 preheat
Stress Strain	ASTM D412	Cured 35' @ 145° C
MIM mix	ASTM D3186	

5955 Scenic Highway • Baton Rouge, LA 70805-2044
800 / 535-9960 • www.lioncopolymer.com

Copo and Carbomix are registered trademarks of Lion Copolymer, LLC
CB1606K issued 10/10; supersedes all previous