


Description

ETHANOX 310 TF (tin-free) antioxidant is a highly effective, noncoloring, odorless antioxidant. It has very low volatility, functions at high process temperatures and provides good long-term protection. ETHANOX 310 TF antioxidant is useful in stabilizing polyolefins and other plastics, elastomers, adhesives, resins, oils, and other organic substrates subject to oxidation. ETHANOX 310 TF antioxidant is approved by the FDA for use in indirect food contact applications*. It can be used in combination with phosphites or thioethers, acid neutralizers, UV stabilizers, and other functional additives, and is free of tin.



**PENTERYTHRITOL TETRAKIS
(3-(3,5-DI-T-BUTYL-4-HYDROXYPHENYL)PROPIONATE)**

Typical Properties*

Form white crystalline powder
Flash point, open cup, °C 280
Molecular weight 1177.7
Melting range, °C 110 -125
Aerated bulk density, g/ml 0.55

**Presented for informational purposes only. To obtain a copy of the sales specifications, FDA status or use guidelines for this product, please contact an Albemarle representative.*

Solubility (g/100 ml at 20 °C)

Acetone 47
Methylene chloride 63
Ethanol 1.5
Toluene 60
n-Hexane 0.3
Water < 0.01
Methanol 0.9

MARKETED BY
**HARWICK STANDARD
DISTRIBUTION CORPORATION**
60 S. Seiberling Street • Akron, Ohio 44305

Shipping Information

50kg fiber drums

Shipping Classifications

Proper shipping name: Not regulated for transportation

Safety and Handling Information

ETHANOX 310 TF antioxidant should be handled with care to prevent contamination of the environment.

Crystalline compounds containing phenolic groups are known to have severe dust explosivity ratings. See material safety data sheet for handling information.

For specific information on the safe handling of this product, please refer to the material safety data sheet. Copies are available on request.

Chemical Registration NumbersCAS: 6683-19-8
MITI: 3-1693**Usage Guidelines**

Please contact an Albemarle representative for pertinent use and application information.

The information presented herein is believed to be accurate and reliable, but is presented without guarantee or responsibility on the part of Albemarle Corporation. It is the responsibility of the user to comply with all applicable laws and regulations and to provide for a safe workplace. The user should consider any health or safety hazards or information contained herein only as a guide, and should take those precautions which are necessary or prudent to instruct employees and to develop work practice procedures in order to promote a safe work environment. Further, nothing contained herein shall be taken as an inducement or recommendation to manufacture or use any of the herein materials or processes in violation of existing or future patents.



MARKETED BY
HARWICK STANDARD
DISTRIBUTION CORPORATION
60 S. Seiberling Street • Akron, Ohio 44305

AMERICAS 451 Florida Street • Baton Rouge, Louisiana 70801-1765 • Tel: 225-388-7402 or 800-535-3030 • Fax: 225-388-7848 **EUROPE** Parc Scientifique Einstein • Rue du Bosquet 9 • B-1348 Louvain-la-Neuve Sud, Belgium • Tel: 32-10-48-1711 • Fax: 32-10-48-1717 **ASIA PACIFIC** 111 Somerset Road #13-03 • Singapore 238164 • Tel: 65-6732-6286 • Fax: 65-6737-4155
ASIA PACIFIC 16th Floor, Fukoku Seimei Building • 2-2-2, Uchisaiwai-cho • Chiyoda-ku, Tokyo 100-0011, Japan • Tel: 81-3-5251-0796 • Fax: 81-3-3500-8623 **ASIA PACIFIC** China World Tower, Room 1317 • No. 1 Jian Guo Men Wai Avenue • Beijing 100004 China • Tel: 86-10-6505-4153 or 86-10-6505-4154 • Fax: 86-10-6505-4150