



BURGESS KE

SURFACE MODIFIED CALCINED ALUMINUM SILICATE

BURGESS KE is a uniquely processed silane modified anhydrous aluminum silicate designed for use in EPR, EPT, crosslinked polyethylene and polyester systems.

BURGESS KE is a very pure, high brightness, low residue, calcined kaolin with a surface that has been chemically transformed by the carefully controlled reaction of an organofunctional silane. This surface conversion permits direct reaction with compatible polymer matrixes in the presence of a peroxide yielding excellent dispersion with minimum work required. The evidence of clay/silane/polymer interaction is demonstrated by increased physical properties such as tensile strength and compression set. KE exhibits excellent wet and dry, initial and long-term electrical characteristics.

Typical Physical Properties

GE Brightness % 90.0

325 Mesh Residue % Max 0.03

Average Particle Size Sedigraph 1.5 μ

Free Moisture % Max 0.5

Specific Gravity 2.63

Refractive Index 1.62

pH (20% Solids) 7.0

Typical Chemical Properties

Loss On Ignition % 0 – 1.0

Silica (SiO₂) % 51.0 – 52.4

Alumina (Al₂O₃) % 42.1 – 44.3

Iron Oxide (Fe₂O₃) % Trace

Titanium Dioxide (TiO₂) % 1.56 – 2.50

Issue Date: TD00F

The suggestions and data contained in this bulletin are based on data which are believed to be reliable. They are offered in good faith, to be applied according to the user's own best judgment. Since operating conditions in the processor's plant are beyond our control, Burgess Pigment Company cannot assume responsibility for any risks or liabilities which may result from the use of its products. Likewise, no liability is assumed for any claimed patent infringement occurring by reason of any method or manner of use, or any product made by a consumer. While the Burgess Pigment Company guarantees the quality of its products, it cannot give any warranty regarding the results obtained by the use thereof.

Distributor

P.O. Box 66 Hickory, Kentucky | 962 State Route 1241, Mayfield, Kentucky 42051
USA | 1.270.247.3042 USA | Fax 270.247.1842 |

