# **TECHNICAL DATA SHEET**

# Iron Oxide Black BK6599

Edition of	2012-12-11			
Туре	Black Pigment-High Performance micronised			
Molecular formula	Fe3O4			
Molecular weight	231.54			
Delivery Form	Powder			
Chemical Class	Synthetic Iron Oxide Fe3O4			
Color Index	Pigment Black 11 (77499)			
CAS No.	1317-61-9			
Use ReCommedation	Coating, Construction, Plastic			

## COLOR VALUES AND TINTING STRENGTH

Reference			Standard: DIN 6174
	<u>Min</u>	<u>Max</u>	Test Method
Reduction with titanium dioxide (1:5)	R-7	/06	No.038.2009-08-01
$\triangle L^{\star}$	-0.5	0.5	
ΔL	-0.5	0.5	
$\triangle a^*$	-0.5	0.5	
$\triangle b^{\star}$	-0.5	0.5	
∆E*ab		0.8	
Binder	R-	05	
Relative tinting strength [%]	97.0	103.0	No.038.2009-08-01

#### **TECHNICAL DATA**

	<u>Min</u>		Max	Test Method
Fe3O4	94			DIN 55913-2
Water soluble substances [%]			0.5	DIN ISO 787-3
Moisture at 105℃ <b>[%]</b>			0.5	DIN ISO 787-2
Oil absorption approx [%]		25		DIN ISO 787-5
Sieve residue on 0.045mm mesh [%]			0.05	DIN 53195
Tinting strengths vs. standard range	97		103	DIN 6174
ΔΕ			0.8	DIN 6174
PH Value	7.0		8.0	DIN ISO 787-9
Density		4.5		DIN ISO 787-10
Tamped Density		1.0		DIN ISO 787-11

### TRANSPORT AND STORAGE

Protect against weathering. Store in a dry place and avoid extreme fluctuations in temperature. Special conditions for opened packaging: Close bags after use to prevent the absorption of moisture and contamination.

#### SAFETY

The product is not classified as dangerous under the relevant EC directives and corresponding national regulations valid in the individual EU member states. It is not dangerous according to transport regulations. In countries outside the EU, compliance with the respective national legislation concerning the classification, packaging, labeling and transport of dangerous substances must be ensured. The information contained in the safety data sheet should be observed. This contains information on handing, product safety and ecology.