# **TECHNICAL DATA SHEET**

## Iron Oxide Yellow YZ1688

Edition of	2012-12-20
Туре	Yellow Pigment-High Performance micronised
Molecular formula	Fe2O3. H2O
Molecular weight	177.71
Delivery Form	Powder
Chemical Class	Synthetic Iron Oxide alpha-FeOOH
Color Index	Pigment Yellow 42(77492)
CAS No.	20344-49-4
Use ReCommedation	Coatings, Construction, Plastic

### **COLOR VALUES AND TINTING STRENGTH**

Reference		;	Standard: DIN 6174
	<u>Min</u>	<u>Max</u>	<b>Test Method</b>
Binder	Test Paste Based On		
	R-0	)5	
Full Shade			No.001, 2001-01-01
<b>△L*</b>	-0.4	0.4	
∆a*	-0.8	8.0	
∆b*	-0.9	0.9	
∆E*ab		1.0	
Reduction with titanium dioxide (1:5)	R-706		No.038, 2009-08-01
$\triangle L^{\star}$	-0.5	0.5	
∆a*	-0.5	0.5	
∆b*	-0.6	0.6	
∆E*ab		8.0	
Binder	R-C	)5	
Relative tinting strength [%]	97.0	103.0	No.038, 2009-08-01

#### **TECHNICAL DATA**

<u>Min</u> <u>Max</u>	Test Method
86	DIN 55913-2
0.5	DIN ISO 787-3
0.5	DIN ISO 787-2
35	DIN ISO 787-5
0.005	DIN 53195
Similar-a little	DIN 6174
0.8	DIN 6174
	86 0.5 0.5 35 0.005 Similar-a little

PH Value	4.5	7.0	DIN ISO 787-9
Loss on Heating 1000 ℃ 1/2h	14.0		DIN 55913-2
Density	4.0		DIN ISO 787-10
Tamped Density	0.6		DIN ISO 787-11

#### STANDARD PACKAGING 20kg/bag

#### TRANSPORT AND STORAGE

Protect against weathering. Store in a dry place and avoid extreme fluctuations in temperature. Special conditions for opened packaging: Close bags after use to prevent the absorption of moisture and contamination.

#### **SAFETY**

The product is not classified as dangerous under the relevant EC directives and corresponding national regulations valid in the individual EU member states. It is not dangerous according to transport regulations. In countries outside the EU, compliance with the respective national legislation concerning the classification, packaging, labeling and transport of dangerous substances must be ensured.

The information contained in the safety data sheet should be observed.

This contains information on handing, product safety and ecology.