

Keltan[®] 3250

Product Description

Amorphous ethylene-propylene rubber with a low ENB (ethylidene norbornene) content and a low Mooney viscosity.

The polymer has a low level of ENB, which results in cure characteristics compatible with butyl rubber. Advantages of EPDM-Butyl blends (compared to 100% butyl) are improved heat- and ozone resistance, lower raw material costs and lower compound costs through increased addition levels of filler and oil.

Typical application areas for the product are inner tubes (blend with butyl rubber) and geo membranes (blend with butyl rubber).

Supply Form

Standard bales.

Raw Material Properties

Property	Nominal Value	Unit	Test Method
Mooney Viscosity ML (1+4) 125°C	33	MU	ISO 289
Ethylene content	55	wt %	ASTM D 3900
ENB content	2.3	wt %	ASTM D 6047
Molecular weight distribution	Narrow		ARLANXEO

Other Product Features

Property	Typical Value	
Specific gravity	0.86	kg/dm ³
Stabilizer	non-staining	
Packaging	Cardboard box; EVA bale wrap; 36 standard bales (900 kg).	

Keltan[®] 3250

Storage Life/Conditions	The product should be stored dry and at temperature < 30 °C. Exposure to light has to be avoided.
Shelf life	36 months from date of production stored at above mentioned conditions.
Product Safety	Relevant safety data and references as well as the possibly necessary warning labels are to be found in the safety data sheet.

These raw material properties are typical and, unless specifically indicated otherwise, are not to be considered as delivery specification.

KELTAN[®] is a Registered Trademark of ARLANXEO Netherlands B.V.

This information and our technical advice – whether verbal, in writing or by way of trials – are given in good faith but without warranty, and this also applies where proprietary rights of third parties are involved. Our advice does not release you from the obligation to verify the information currently provided – especially that contained in our safety data and technical information sheets – and to test our products as to their suitability for the intended processes and uses. The application, use and processing of our products and the products manufactured by you on the basis of our technical advice are beyond our control and, therefore, entirely your own responsibility. Our products are sold in accordance with the current version of our General Conditions of Sale and Delivery.

Issue number: LXS 12 / Date of issue: October 17, 2014 / Previous issue from April 9, 2014 / Information current as of date of issue. Please contact your ARLANXEO representative to determine if this publication has been revised.