



## Product Data Sheet

### *Picco* 6100 Hydrocarbon Resin

*Picco* 6100 hydrocarbon resin is one in a series of low molecular weight, non-polar, amber colored thermoplastic resins produced from petroleum-derived monomers, ranging in softening point from medium to high.

#### List of Applications

- Reinforcing agent for plastics and adhesives
- Rubber compounding extender
- Tackifier

#### Sales Specifications

Property	Minimum	Maximum	Test Method
Softening point, °C, Ring & Ball	98	108	CASPI-A-AN-G-PP-085
Color, Gardner, 50% in Toluene	—	14	CASPI-A-AN-G-AC-100

#### Compatibility and Solubility

*Picco* 6100 hydrocarbon resin is characterized by excellent resistance to acids, alkalis, and moisture; by good color stability; and, when formulated with elastomers, by a good balance of flex, tear, and adhesion properties.

*Picco* 6100 is compatible in useful proportions with styrene-butadiene rubber (SBR), rosin, modified rosins and rosin esters, alkyds and drying oils, polar elastomers, epoxy resins, and chlorinated rubber. It is soluble in aromatic, aliphatic, and chlorinated hydrocarbons; low kauri-butanol (KB) aliphatic ink oils; benzyl alcohol; cyclohexanol; methyl ethyl ketone. *Picco* 6100 is insoluble in lower alcohols, acetone, and ethylene glycol.

#### FDA Status

*Picco* 6100 complies with requirements of the U.S. Food and Drug Administration (FDA) for use as specified in the Code of Federal Regulations, Title 21, subject to the limitations and requirements of each regulation under the following Section(s):

175.105 Adhesives

177.2600 Rubber Articles Intended for Repeated Use (not to exceed 30% by weight of rubber product)

The formulator must comply with all requirements of the FDA regulations, including conditions of use and extractive tolerances of the total compound or formula.

#### Packaging

Flake, in multi-wall kraft paper bags (50 lbs, 22.7 kg net wt) stacked 40 bags per pallet.

#### Additives

*Picco* 6100 hydrocarbon resin is stabilized with an antioxidant.

## Picco 6100 Hydrocarbon Resin

### Typical Properties

Property Data	Typical Values
Softening Point, Ring & Ball	104°C
Gardner Color, 50% in Toluene	11°C
Cloudpoint, MMAP	30°C
Cloudpoint, DACP	10°C
Cloudpoint, OMS	
Initial	75°C
Full	58°C
Density @ 25°C	1.08 kg/L (9.0 lb/gal)
Glass Transition, $T_g$ , Midpoint	46°C
Melt Viscosity	
10 poise	167°C
100 poise	141°C
1000 poise	118°C
Molecular Weight (Gel Permeation Chromatography)	
$M_n$	540
$M_w$	1800
$M_z$	5300

### Storage

Flaked and crushed forms of resins may fuse, block, or lump during hot weather months, if stored near steam pipes or other sources of heat, and if stored for prolonged periods. Because of the extremely large surface area they present, flaked and crushed forms of resins are prone to gradual oxidation, some more so than others. This could result in darkening and/or it could have an adverse effect on solubility of the resin in organic solvents. Accordingly, it is strongly recommended that strict control of inventory be observed at all times, taking care that the oldest material is used first.

#### ■ NORTH AMERICA

##### Eastman Chemical Company Corporate Headquarters

P.O. Box 431  
Kingsport, TN 37662-5280 U.S.A.

Telephone:  
U.S.A. and Canada, 800-EASTMAN (800-327-8626)  
Other Locations, (1) 423-229-2000  
Fax: (1) 423-229-1064

[www.eastman.com](http://www.eastman.com)

*Eastman Chemical Company and its marketing affiliates shall not be responsible for the use of this information, or of any product, method, or apparatus mentioned, and you must make your own determination of its suitability and completeness for your own use, for the protection of the environment, and for the health and safety of your employees and purchasers of your products. No warranty is made of the merchantability or fitness of any product, and nothing herein waives any of the Seller's conditions of sale.*

Eastman and Picco are trademarks of Eastman Chemical Company.

© Eastman Chemical Company, 2004.

MARKETED BY  
**HARWICK STANDARD  
DISTRIBUTION CORPORATION**

60 S. Seiberling Street • Akron, Ohio 44305

WA-95  
January 2004