

DUOPRIME® OILS

Date 02/08

- DESCRIPTION:** Duoprime Oils are produced using severe hydrogenation of paraffinic feedstocks utilizing a unique two stage catalytic hydrotreating process. Our DUOTREAT hydrogenation process saturates all aromatic and olefinic compounds while effectively eliminating nitrogen and sulfur containing compounds. The finished products are water white mineral oils of the highest purity. Stabilized with Vitamin E. They are available in a wide range of viscosity grades.
- QUALITIES:** Duoprime Oils exceed requirements set forth in the U.S. FDA regulations 21 CFR 172.878 for use in or on food for human consumption, and 21 CFR 178.3620 (a) for use as a component of nonfood articles intended for use in contact with food for human consumption.
- Duoprime Oils meet the current standards of the National Formulary (NF) or US Pharmacopeia (USP), and are registered as 3H and H1 lubricants for direct and incidental food contact by NSF, for use in food plants under the jurisdiction of the USDA. Duoprime Oils 200 and 350 are certified to ANSI/NSF Standard 60, Drinking Water Treatment Chemicals – health effects for use with potable water systems.
- Duoprime Oils are certified as Kosher (passover) with the Union of Orthodox Jewish Congregations of America ®.
- APPLICATIONS:** Duoprime Oils can be used in cosmetics & pharmaceuticals, suntan lotions, baby oils, bath oils, as a base for ointments, as a pelletizing aid, and as a drug processing agent.
- They can be used in the fibers, plastics and resins area as a process aid, a diluent, a pigment dispersant, and textile fiber lubricant. In the food processing area, they can be used as a release agent on grills, bakery pans and dough dividers, cutters, knives, meat packers benches, boards, trays, hooks and other food processing equipment.
- They can be used for coatings for fruits and vegetables, defoamer, shell egg spray, a lubricant and rust preventative for food processing machinery.

MARKETED BY
**HARWICK STANDARD
DISTRIBUTION CORPORATION**
60 S. Seiberling Street • Akron, Ohio 44305

SCHUMANN / STEIER, INC.

2525 Ponce de Leon Blvd., Suite 650 • Coral Gables, Florida 33134 • Tel: (305) 442-2999 Fax: (305) 442-9666

TYPICAL PROPERTIES:

DUOPRIME® OILS

VIS Grade	70	90	100	200	300	350	500
Material Code	42006	42008	42030	42010	42013	42015	42017
Gravity, ASTM D 287, °API	34.0	33.7	33.0	31.7	31.0	30.7	30.1
Specific Gravity at 25°C, ASTM D 1298	0.850	0.854	0.855	0.862	0.866	0.867	0.870
Flash Point COC, ASTM D 92, °F (°C)	70 (188)	385 (196)	385 (196)	415 (213)	440 (227)	450 (232)	490 (254)
Pour Point, ASTM D 97, °F (°C)	-10 (-23)	+10 (-12)	+10 (-12)	+10 (-12)	+10 (-12)	+10 (-12)	+10 (-12)
Viscosity, ASTM D 445, cSt at 40°C	13.9	16.0	20.0	38.8	58.0	67.5	105.5
cSt at 100°C	3.0	3.4	4.2	6.2	7.2	8.7	12.0
ASTM D 2161, SUS at 100°F	73	86	105	200	300	350	560
SUS at 210°F	36.0	38.0	42.0	46.4	52.4	55.0	67.0
Color, Saybolt, ASTM D 156	+30	+30	+30	+30	+30	+30	+30
NF/USP	NF	NF	NF	USP	USP	USP	USP
Kosher	Ⓚ	Ⓚ	Ⓚ	Ⓚ	Ⓚ	Ⓚ	Ⓚ
NSF	3H, H1	3H, H1	3H, H1	3H, H1	3H, H1	3H, H1	3H, H1
NSF/ANSI	-	-	-	STD 60	-	STD 60	-
FDA, 21 CFR							
172.878	✓	✓	✓	✓	✓	✓	✓
178.3620 (a)	✓	✓	✓	✓	✓	✓	✓
USDA Shell Egg Oil	✓	✓	-	-	-	-	-

Note: All oils above are colorless (Saybolt +30 Color), odorless and tasteless and surpass requirements of FDA and U.S. Pharmacopeia (USP) and National Formulary (NF) standard for Neutrality, Sulfur Compounds, Solid Paraffins, Readily Carbonizable Substances and limit of Polynuclear Compounds (UV test) and Residual Solvents.

Other viscosity grades available, consult your sales manager.

MARKETED BY
**HARWICK STANDARD
 DISTRIBUTION CORPORATION**
 60 S. Seiberling Street • Akron, Ohio 44305



Harwick Standard Distribution Corporation

Plasticizers

Harwick Standard offers a broad line of plasticizers to meet the needs of both rubber compounders and flexible PVC formulators. By offering a large range of products, we provide our customers the versatility of identifying a plasticizer family that is effective with various polymers, and gives several product options from which to choose for optimum performance characteristics - from general use to most demanding requirements.

Harwick Standard's experienced technical and sales staff can assist in selecting the best plasticizer to meet your requirements. Please contact us for assistance with your compounding needs.

Non-Phthalate C-9

Tradename(s)	Chemical Name	Polymer Usage	General Purpose	Low Temperature/ Flexibility	Low Volatility	Low Extraction	Heat Aging Resistance	High Solvating	Miscellaneous
Polycizer® DHIN	1-2 cyclohexane dicarboxylic acid diisononyl ester	R-1,2/P-1	✓						Performance similar to DOP in NBR compounds

Adipates

Tradename(s)	Chemical Name	Polymer Usage	General Purpose	Low Temperature/ Flexibility	Low Volatility	Low Extraction	Heat Aging Resistance	High Solvating	Miscellaneous
Polycizer® DOA	Di-2 ethylhexyl adipate	R-1,2/P-1,2	✓	✓					FDA, low water extraction, UV stability
Merrol® 4206 (DBEA)	Dibutoxyethyl adipate	R-1,2,3/P-2		✓					
Polycizer DBEEA Merrol 4226	Dibutoxyethoxyethyl adipate	R-1,2,3		✓	✓	✓	✓		

Azelates

Tradename(s)	Chemical Name	Polymer Usage	General Purpose	Low Temperature/ Flexibility	Low Volatility	Low Extraction	Heat Aging Resistance	High Solvating	Miscellaneous
Merrol DOZ-E	Di-2 ethylhexyl azelate	R-1,2/P-1,2	✓	✓	✓				Excellent low temp

Polymer Usage Key

R-1	NBR, NBR/PVC
R-2	CR, CPE, CSM
R-3	ECO, Fluoroelastomers, Polyacrylates

Polymer Usage Key

P-1	PVC
P-2	PVAC, PS, ABS, Cellulosics
P-3	Eng, Resins, Polyester, Alloys

Benzoates

Tradename(s)	Chemical Name	Polymer Usage	General Purpose	Low Temperature/ Flexibility	Low Volatility	Low Extraction	Heat Aging Resistance	High Solvating	Miscellaneous
Benzoflex® 9-88	Dipropylene glycol dibenzoate	R-1/P-1,2			✓			✓	Polyurethanes
Benzoflex 50	Diethylene/ dipropylene glycol dibenzoate	R-1/P-1,2			✓			✓	Water-based adhesives
Benzoflex 2088	Diethylene glycol dibenzoate, triethylene glycol dibenzoate, dipropylene glycol dibenzoate	R-1/P-1,2			✓	✓		✓	High solvator, low VOC's, FDA

Chlorinated Paraffins

Tradename(s)	Chemical Name	Polymer Usage	General Purpose	Low Temperature/ Flexibility	Low Volatility	Low Extraction	Flame Resistance	High Solvating	Miscellaneous
Chloro Flo/ Paroil Series	Liquid chlorinated paraffins	R-2/P-1	✓		✓		✓		

Mono-Esters

Tradename(s)	Chemical Name	Polymer Usage	General Purpose	Low Temperature/ Flexibility	Low Volatility	Low Extraction	Heat Aging Resistance	High Solvating	Miscellaneous
Polycizer Butyl Oleate	N-butyl oleate	R-2/P-2		✓					Primary light color plasticizer for polychloroprene
Polycizer MO	Vegetable Oil	R-2		✓	✓		✓	✓	Low & high temp for polychloroprene
Plasticizer OLN	Oleyl nitrile	R-1				✓		✓	Low & high temp for polychloroprene
Natoflex® IOT	Isooctyl tallate	R-1,2	✓	✓					
Merrol 818T	Alkyl tallate	R-1/P-2	✓	✓					

Polymer Usage Key

R-1	NBR, NBR/PVC
R-2	CR, CPE, CSM
R-3	ECO, Fluoroelastomers, Polyacrylates
P-1	PVC
P-2	PVAC, PS, ABS, Cellulosics
P-3	Eng, Resins, Polyester, Alloys

Petroleum Process Oils

Tradename(s)	Chemical Name	Polymer Usage	General Purpose	Low Temperature/ Flexibility	Low Volatility	Low Extraction	Heat Aging Resistance	High Solvating	Miscellaneous
Stan-Lube Series	Paraffinic oils	Non-polar	✓						Light color, good for EPRs
Stan-Plas Series	Naphthenic oils	R-1	✓						General Processability
Duoprime® Series	White oils	Non-polar	✓						FDA

Phosphate Esters

Tradename(s)	Chemical Name	Polymer Usage	General Purpose	Low Temperature/ Flexibility	Low Volatility	Low Extraction	Flame Resistance	High Solvating	Miscellaneous
Lindol®	Tricresyl phosphate	P-1,2	✓		✓		✓	✓	
Phosflex® 41L Merrol 521	Isopropylated triaryl phosphate	R-1,2/P-1					✓		
Phosflex T-BEP	Tributoxyethyl phosphate	R-1,2,3/P-1,2		✓			✓	✓	
Phosflex 71-B	Butylated triphenyl phosphate	R-1,2/P-1					✓		
Phosflex 362	2-ethyhexyl diphenyl phosphate	R-1,2/P-1,2					✓		
Phosflex 390	Isodecyl diphenyl phosphate	R-1,2/P-1,2					✓		

Disclaimer of Liability

The information and recommendations contained herein are based upon data that are believed to be accurate and reliable to be the best of Harwick's knowledge and belief. Application and performance information are provided only as a guide, since the conditions of use are beyond Harwick's control. No warranty is made of the merchantability or fitness for a particular purpose, and Harwick Standard Distribution Corporation shall not be liable for any cost, loss, damage, or liability arising from the failure to achieve a particular result by the application of any method or process that is recommended herein.

Polymer Usage Key

R-1	NBR, NBR/PVC
R-2	CR, CPE, CSM
R-3	ECO, Fluoroelastomers, Polyacrylates
P-1	PVC
P-2	PVAC, PS, ABS, Cellulosics
P-3	Eng. Resins, Polyester, Alloys

Phthalates

Tradename(s)	Chemical Name	Polymer Usage	General Purpose	Low Temperature/ Flexibility	Low Volatility	Low Extraction	Heat Aging Resistance	High Solvating	Miscellaneous
Merrol DAP	Diallyl phthalate	R-1,2/P-3						✓	Co-curing
Polycizer DBP Merrol DBP	Di-n-butyl phthalate	R-1,2/P-1,2	✓					✓	Good emollient for cosmetics
Polycizer DIDP	Diisodecyl phthalate	R-1,2/P-1,2			✓	✓			Also E grade
Polycizer DINP Merrol DINP	Disisononyl phthalate	R-1,2/P-1,2			✓				
Polycizer DOP Merrol DOP	Di-2-ethylhexyl phthalate	R-1,2/P-1,2	✓						
Polycizer DUP	Diundecyl phthalate	R-1,2/P-1,2		✓	✓		✓		Low fogging Also CA grade

Polymeric

Tradename(s)	Chemical Name	Polymer Usage	General Purpose	Low Temperature/ Flexibility	Permeability	Migration Resistance	Low Extraction	Heat Aging	Miscellaneous
Admex® P-27	Polyester adipate	R-1/P-1,2				✓			High purity, good electrical properties
Admex 409	Polyester adipate	R-1/P-1,2	✓			✓		✓	Good electrical properties
Admex 412	Polyester adipate	R-1/P-1		✓	✓				Low viscosity, easy processing
Amdex 429	Polyester adipate	R-1,2/P-1,2				✓			Non-fogging, humidity resistance
Admex 523	Mixed polyester	R-1/P-1,2	✓			✓	✓		Low viscosity
Admex 760	Polyester adipate	R-1,2/P-1,2			✓	✓			Excellent permanence, low water extractability
Admex 761	Polyester adipate	R-1/P-1,2					✓		
Admex 770	Mixed polyester	R-1,2/P-1,2			✓	✓			Excellent weatherability (decals)
Admex 775	Mixed polyester	R-1/P-1,2							Excellent resistance to aqueous & organic solvents
Admex 910-001	Mixed polyester	R-1/P-1,2					✓		Low water extraction
Admex 1723	Mixed polyester	R-1/P-1,2			✓				Printability
Admex 2632	Mixed polyester	R-1/P-1,2	✓						FDA

Polymeric (continued)

Tradename(s)	Chemical Name	Polymer Usage	General Purpose	Low Temperature/ Flexibility	Permeability	Migration Resistance	Low Extraction	Heat Aging	Miscellaneous
Admex 6187	Polyester adipate	R-1/P-1,2				✓	✓		Solvent & oil resistance
Admex 6985	Polyester adipate	R-1/P-1,2				✓	✓	✓	Very low volatility
Admex 6994	Mixed polyester	R-1/P-1,2				✓			Mar resistance, low fogging
Admex 6995	Polyester adipate	R-1/P-1,2			✓				UV weatherability
Admex 6996	Polyester adipate	R-1/P-1,2		✓					Printability
Tradename(s)	Chemical Name	Polymer Usage	General Purpose	Low Temperature/ Flexibility	Low Volatility	Low Extraction	Heat Aging Resistance	High Solvating	Miscellaneous
Merrol P-6320	Polyester adipate	R-1,2/P-1		✓		✓			Solvent & oil resistance, low temp flexibility
Merrol P-6412	Polyester adipate	R-1,2/P-1,2				✓			Medium viscosity, FDA
Merrol P-6410	Polyester adipate	P-1,2			✓	✓			
Merrol P-6420	Polyester adipate	P-1				✓			Good color

Sebacates

Tradename(s)	Chemical Name	Polymer Usage	General Purpose	Low Temperature/ Flexibility	Low Volatility	Low Extraction	Heat Aging Resistance	High Solvating	Miscellaneous
Polycizer DBS	Di-n-butyl sebacate	R-1,2/P-1,2		✓				✓	FDA
Polycizer DOS Merrol DOS	Di-2-ethylhexyl sebacate	R-2/P-1,2	✓	✓		✓			Low temp greases & caulks

Harwick Standard Distribution Corporation

www.harwickstandard.com

330-798-9300

Polymer Usage Key

R-1	NBR, NBR/PVC
R-2	CR, CPE, CSM
R-3	ECO, Fluoroelastomers, Polyacrylates
P-1	PVC
P-2	PVAC, PS, ABS, Cellulosics
P-3	Eng, Resins, Polyester, Alloys

Specialty

Tradename(s)	Chemical Name	Polymer Usage	General Purpose	Low Temperature/ Flexibility	Permeability	Migration Resistance	Low Extraction	Heat Aging	Miscellaneous
Plasticizer SC-B	Triethyleneglycol dicaprate/caprylate	R-1,2,3		✓				✓	FDA
Plasticizer SC-E	Triethyleneglycol di 2-ethylhexanoate	R-1,2,3		✓					Flexibility over a wide temp range
Hercoflex® 600	Pentaerythritol ester of fatty acids	R-1,2		✓	✓	✓	✓	✓	Excellent low and high temp
Hercoflex 707, 707A	Pentaerythritol ester of fatty acids	R-1,2		✓	✓	✓	✓	✓	Excellent low and high temp
Polycizer ESO Merrol E-68	Epoxidized soybean oil	R-1/P-1,2,3			✓	✓		✓	Good heat stabilizer

Trimellitates

Tradename(s)	Chemical Name	Polymer Usage	General Purpose	Low Temperature/ Flexibility	Permeability	Migration Resistance	Low Extraction	Heat Aging	Miscellaneous
Polycizer TOTM	Tri-2-ethylhexyl trimellitate	R-1,2/P-1,2			✓		✓	✓	Also E&CA grades, excellent water resistance
Merrol 810TM-E	Tri(n-octyl/n-decyl) trimellitate	R-2		✓	✓		✓	✓	Oxidation resistance, excellent water resistance
Polycizer TINTM	Trisononyltrimellitate	R-1,2/P-1,2			✓	✓	✓	✓	



Harwick Standard Distribution Corporation

60 South Seiberling Street

P.O. Box 9360

Akron, OH 44305-0360

Phone: 330-798-9300

Fax: 330-798-0214

Technical Fax: 330-798-9328

Sales Fax: 330-798-4089

www.harwickstandard.com

Polymer Usage Key	
R-1	NBR, NBR/PVC
R-2	CR, CPE, CSM
R-3	ECO, Fluoroelastomers, Polyacrylates
P-1	PVC
P-2	PVAC, PS, ABS, Cellulosics
P-3	Eng, Resins, Polyester, Alloys

® Permission to use registered tradename(s) of products with such registration indicated has been granted by the rightful owners.