



5955 Scenic Highway • Baton Rouge, LA 70805-2044
800 / 535-9960 • www.lioncopolymer.com

Royalene[®] 563 EPDM

Product Data

"A General Purpose Polymer for Hose and Extruded Profiles "

Unique Features

- ▶ Friable bale provides excellent degree of dispersion
- ▶ Highly extendable
- ▶ Excellent low temperature properties
- ▶ Excellent compression set
- ▶ Fast cure rate

Applications

- ▶ Hose
- ▶ Extruded Profiles
- ▶ Mechanical Goods

Raw Polymer Properties and Specifications

	Test Method*	Min.	Max.	Typical
Mooney Viscosity, ML (1+4)/125°C (Unmilled)	ZS 1220B	70	80	—
E/P Weight Ratio.....	ZS 1231	—	—	60/40
ENB, Weight %	ZS 1222	—	—	4.5
Molecular Weight Distribution	ZS 1296A	—	—	Medium
Volatile Matter, Weight %.....	ZS 1008K	—	1.0	—
Stabilizer	—	—	—	Non-Staining
Specific Gravity, g/cc	ASTM D-792	—	—	0.87
Color	ZS 1072A	—	—	Off White
Physical Form, lbs/bale.....	—	—	—	59.5 (27 kg) (Friable bale)

* Company Test Methods
R-563/mef

ASP-R175G
rfo-04/13

Notice: All information supplied by or on behalf of Lion Copolymer in relation to its products, whether in the nature of data, recommendations or otherwise, is supported by research and believed reliable, but Lion Copolymer assumes no liability whatsoever in respect of application, processing or use made of the aforementioned information or products, or any consequence thereof. The buyer undertakes all liability in respect of the application, processing or use made of the aforementioned information or product, whose quality and other properties he shall verify, or any consequence thereof. No liability whatsoever shall attach to Lion Copolymer for any infringement of the rights owned or controlled by a third party in intellectual, industrial or other property by reason of the application, processing or use of the aforementioned information or products by the buyer.