


Product Data

SANTOFLEX 6PPD



N-(1,3-Dimethylbutyl)-N'-phenyl-p-phenylenediamine

CAS Reg. No.: 793-24-8

Molecular weight: 268

FUNCTION

Santoflex 6PPD functions as a powerful antioxidant and antiozonant for natural and synthetic elastomer compounds and as a synthetic polymer stabilizer. Santoflex 6PPD provides protection against fatigue degradation in both static and dynamic operating conditions.

MAJOR APPLICATIONS AND PROPERTIES

- Santoflex 6PPD applications include the use in pneumatic tire components, solid tires, belts, hoses, cables, automotive mounts, bushings and general mechanical products that are exposed to continuous and intermittent dynamic operating conditions and require protection from ozonation.
- Santoflex 6PPD provides powerful antiozonant and antioxidant properties with excellent high temperature, fatigue and flex resistance to rubber compounds.
- It gives efficient stabilization for a wide range of solution and emulsion polymers.
- Santoflex 6PPD is a more active antioxidant than quinoline or diphenylamine based antioxidants.
- Santoflex 6PPD gives better long term fatigue resistance and ozone protection than Santoflex IPPD. Due to its specific molecular structure and higher rubber solubility, it is less affected by environmental variables, such as heat or leaching, leading to greater durability.
- Santoflex 6PPD gives rubber protection against catalytic degradation by copper and other heavy metals.
- The product has no negative effects on compound adhesion to textiles or steel cord up to levels of 2 phr. Above this concentration it may bloom and interfere with ply to ply and ply to cord adhesion.
- It will discolor compounds and cause severe contact and migration staining.
- Santoflex 6PPD is regulated for use in articles in contact with food as specified under BgVV XXI, Categories 3-4. Santoflex 6PPD is not regulated for use in FDA food contact applications.

COMPOUNDING INFORMATION

Add 1-3 phr of Santoflex 6PPD to rubber compounds for resistance to ozone and flex fatigue. Increasing the concentration, increases the level of protection. To provide maximum performance in static applications include a blended wax in the compound formulation, appropriately chosen for the application's temperature range. Santoflex 6PPD can also be used for oxidation resistance alone. Its antioxidant performance is maximized at 0.5 phr. Higher levels actually reduce antioxidant protection even though ozone and flex fatigue resistance increase with higher levels.

Typical use information (phr):

| | Tire sidewall | Brassed steel-cord skim | NR/SBR conveyor belt cover | NR/SBR V-belt | NR engine mount |
|-----------------|---------------|-------------------------|----------------------------|---------------|-----------------|
| Santoflex 6PPD | 2 - 4 | 2 | 1 - 2 | 2 | 1 - 2 |
| Flectol TMQ | 1 - 2 | -- | 1 | -- | 0 - 1 |
| Antiozonant wax | 1 - 3 | -- | -- | -- | -- |

Note: No PPD should be used at levels less than 1 phr in surface applications, as the ozone cracking pattern produced can lead to catastrophic failure.

Adding Flectol TMQ will maintain a compound's resistance to oxidation as well as protect Santoflex 6PPD from oxidizing, thus further enhancing long term performance. To protect NBR compounds from ozone attack use 4 phr of Santoflex 6PPD. It will also help protect polychloroprene but can reduce bin storage stability. To stabilize solution or emulsion polymerized elastomers add 0.3 to 0.6% (dry basis) of Santoflex 6PPD.

HANDLING PRECAUTIONS

For detailed information on toxicological properties and handling precautions please refer to the current Safety Data Sheet. This information sheet can be downloaded from our web site or requested from the nearest Flexsys office and should be consulted before handling this product.

STORAGE RECOMMENDATIONS

Store Santoflex 6PPD pastilles in single stacked pallets in a cool, dry, well ventilated area, avoiding exposure of the packaged product to direct sunlight. Double stacking of palletized material and/or exceeding 35°C can result in unusual compaction of product.

Store Santoflex 6PPD liquid in a covered vessel between 50°C and 60°C. If material is to be stored for greater than 30 days or at temperature higher than 60°C the vessel should contain a nitrogen blanket to prevent the product from oxidizing, which will reduce its usefulness as an antiozonant. Do not store material above 75°C for more than 90 days. In bulk storage, continuous circulation will help minimize temperature gradients in the tank and reduce heating element fouling, thus maximizing the product's consistency.

PRODUCT INFORMATION

| Santoflex 6PPD Product form | liq liquid | pst pastilles | |
|---------------------------------------|------------------------|---|--------------------|
| <u>PRODUCT SPECIFICATIONS</u> | | | <u>Test method</u> |
| Appearance | purple brown liquid | off white to dark purple brown pastilles | FF97.5 |
| Purity (GC) | (%) min. 95.0 | 95.0 | FGC97.10 |
| Heat loss | (%) max. 0.5 | 0.5 | FG97.7 |
| Ash | (%) max. 0.1 | 0.1 | FG90.9 |
| <u>TYPICAL PROPERTIES</u> | | | |
| Melting point, final | (°C) 46-51 | 46-51 | |
| Viscosity at 60°C | (cSt) 27-38 | 27-38 | |
| Specific gravity at 60/15°C | 0.986-1.000 | 0.986-1.000 | |

MARKETED BY
HARWICK STANDARD
DISTRIBUTION CORPORATION
 60 S. Seiberling Street • Akron, Ohio 44305

For further information please contact your local Flexsys office or regional Flexsys headquarters:

| | | | | |
|-----------------------|---|-----------------|------------------|---------------|
| Regional Headquarters | : | Brussels | Akron | Singapore |
| Tel. | : | +32 2 714 32 11 | +1 330 666 41 11 | +65 872 28 08 |
| Fax | : | +32 2 714 32 32 | +1 330 668 83 45 | +65 872 28 18 |

All product names are registered trade marks.

6PPD3.AD/1000

The information and recommendations in this publication are provided without warranty as to completeness, correctness or suitability for any particular purpose. The user of this publication assumes responsibility for and Flexsys shall not be liable for any injury, loss or damage arising from any use or reliance upon its contents.

©Copyright Flexsys 2000.

page 2 of 2