




ISO 9001:2008 REGISTERED

CTP

Chemical Name: N-(Cyclohexylthio)phthalimide

Structure



Molecular Weight: 261.3

Class: Retarder

CAS#: 97-74-5

CTP is an inhibitor that when used in an elastomer compound delays the onset of vulcanization. It is most effective when used with sulfenamides, but may be used with all classes and work best when used in NR, NBR, and SBR. It is a true retarder, as it only affects the cure, not the modulus development. CTP is non-staining and only slightly discoloring when used in light colored compounds

CTP is typically used with NR, IR, SBR, and NBR as it is most active but also maybe used in EPDM, IIR, and CR.

CTP has typical properties of: Specific Gravity @ 1.30; Melt Point @ 88°C, and is available in a white crystal or oil treated powder form.

12/23/14

HARWICK STANDARD MAKES NO WARRANTIES, EXPRESS OR IMPLIED, WITH RESPECT TO THE GOODS OR USES OF THE GOODS OR PERFORMANCE OF THE GOODS AND MAKES NO WARRANTIES OF THE FITNESS FOR PARTICULAR PURPOSE OR MERCHANTABILITY. BUYER ACKNOWLEDGES THAT HARWICK STANDARD WILL NOT BE LIABLE FOR CONSEQUENTIAL, INCIDENTAL, DIRECT OR SPECIAL DAMAGES ARISING, DIRECTLY OR INDIRECTLY, IN RESPECT TO SUCH GOODS OR THE USE OR FAILURE TEHEREOF, WHETHER BASED ON BREACH OF WARRANTY, NEGLIGENCE, STRICT LIABILITY IN TORT OR OTHERWISE.

HARWICK STANDARD DISTRIBUTION CORPORATION

60 S. SEIBERLING ST. • P.O. BOX 9360 • AKRON, OH 44305-0360 • U.S.A.
PHONE: (330) 798-9300 • FAX: (330) 798-0214
WWW.HARWICKSTANDARD.COM