

## THERBAN<sup>®</sup> LT 2157

### Product Description

A partially hydrogenated butadiene acrylonitrile ter-polymer for applications requiring good flexibility at low temperature. Designed primarily for dynamic applications requiring excellent resistance to heat, ozone and good resistance to non polar hydrocarbon fluids. Sulfur curing systems are used for improved dynamic properties and adhesion to steel and textile reinforcing materials. However, peroxide/coagent systems can be used for improved resistance to heat and compression set.

### Supply Form

Bales

### Raw Material Properties

Property	Nominal Value	Unit	Test Method
Mooney Viscosity ML (1+4) 100°C	70 ± 7	MU	ISO 289/ASTM D 1646
Acrylonitrile content	21 ± 1.5	wt %	ISO 24698-1
Residual double bonds	5.5 ± 1.0	%	IR Spectroscopy
Volatile matter	≤ 0.49	wt %	ISO 248/ASTM D 5668

### Other Product Features

Property	Typical Value		
Specific gravity	0.96		
Total Ash	≤ 0.9	wt %	ISO 247/ASTM D 5667
Packaging	25 kg bales wrapped in blue PE film, strippable / dispersible (melting point of film = 85 - 110°C, Vicat softening point = 71°C, 0.05 mm thick); pallets of 20 bales (500 kg)		
Shelf life	36 months from date of production at temperatures not exceeding 35°C in dry conditions; exposure to light has to be avoided		
Product Safety	Relevant safety data and references as well as the possibly necessary warning labels are to be found in the safety data sheet.		

These raw material properties are typical and, unless specifically indicated otherwise, are not to be considered as delivery specification.

## THERBAN<sup>®</sup> LT 2157

THERBAN<sup>®</sup> is a Registered Trademark of LANXESS Deutschland GmbH

This information and our technical advice - whether verbal, in writing or by way of trials - are given in good faith but without warranty, and this also applies where proprietary rights of third parties are involved. Our advice does not release you from the obligation to check its validity and to test our products as to their suitability for the intended processes and uses. The application, use and processing of our products and the products manufactured by you on the basis of our technical advice are beyond our control and, therefore, entirely your own responsibility. Our products are sold in accordance with the current version of our General Conditions of Sale and Delivery.

Issue number: LXS 06 / Date of issue: January 01, 2010 / Previous issue from August 04, 2009 / Information current as of date of issue. Please contact your LANXESS representative to determine if this publication has been revised.