

# Thermolite® 108

## Butyltin PVC Heat Stabilizer

### Description

Thermolite 108 is a general purpose, butyltin mercaptide PVC heat stabilizer. It is excellent in preserving compound color hold, even under the most severe processing conditions. Thermolite 108 heat stabilizer is a clear liquid and is completely compatible with all PVC resins and formulation additives.

### General Characteristics

Properties	Typical Values
Form	Clear Oily Liquid, Water White
Color (Gardner)	1
Viscosity, cs (@25°C)	45
Specific Gravity (@25°C)	1.12
Refractive Index	1.50
% Tin	17.9

### Benefits

The advantages of using Thermolite 108 heat stabilizer in PVC formulations include:

- Good early color hold.
- Outstanding long term dynamic stability.
- Excellent regrind stability.
- Low odor.
- Versatile – suitable for injection molding and twin and single screw extrusion applications.
- Excellent weatherability for outdoor PVC building products applications.

### Applications

Thermolite 108 heat stabilizer may be used in a wide variety of applications, but primarily in PVC compounds used in the manufacture of bottles, film or sheet.

### Typical Formulations

Injection Molding (Fittings)	Use Level (phr)
PVC Resin (K-55 to K-58)	100.0
Thermolite 108	1.5 – 2.0
Calcium Stearate	1.0 – 1.5
Paraffin Wax (165°F mp)	1.0 – 1.5
Acrylic Process Aid	1.0 – 1.5
Acrylic Process Aid (Metal Release)	0.0 – 0.5
MBS Impact Modifier	0.0 – 8.0
Calcium Carbonate (0.8 µm)	2.0 – 5.0
Titanium Dioxide	3.0 – 5.0

**In US**  
 PMC Organometallics, Inc.  
 The PMC Group Building  
 1288 Route 73, Suite 401  
 Mount Laurel, NJ 08054

Customer Service  
 1.855.638.2549  
 (1.855.METALIX)  
 Fax 1.856.638.2157

**In Europe**  
 PMC Vlissingen B.V.  
 C/o PMC OUVRIE  
 44 rue Albert Einstein  
 62220 CARVIN  
 FRANCE

Customer Service  
 33(0)3.91.83.71.56  
 Fax 33(0)3.91.83.71.92

The information contained herein is correct to the best of our knowledge. Your attention is directed to the pertinent Material Safety Data Sheets for the products mentioned herein. All sales are subject to PMC Organometallics Inc.'s standard terms and conditions of sale, copies of which are available upon request and which are part of PMC Organometallics Inc.'s invoices and/or order acknowledgements. Except as expressly provided in PMC Organometallics Inc.'s standard terms and conditions of sale, no warranty, expressed or implied, including warranties of merchantability or fitness for a particular purpose, is made with respect to the products described herein. Nothing contained herein shall constitute permission or recommendation to practice any invention covered by a patent without a license from the owner of the patent.

<b>Weatherable Injection Molding (Fittings)</b>	<b>Use Level (phr)</b>
PVC Resin (K-55 to K-58)	100.0
Thermolite 108	1.5 – 2.0
Calcium Stearate	0.7 – 1.5
Paraffin Wax (165°F mp)	0.7 – 1.5
Acrylic Impact Modifier	2.0 – 3.0
Acrylic Process Aid	0.7 – 2.0
Calcium Carbonate (0.8 µm)	3.0 – 5.0
Titanium Dioxide	9.0 – 10.0

  

<b>Clear Extruded Sheet</b>	<b>Use Level (phr)</b>
PVC Resin (K-60)	100.0
Thermolite 108	0.8 – 1.7
Internal Lubricants	0.6 – 1.0
Acrylic Process Aid	1.0 – 2.0
Acrylic Process Aid (Metal Release)	0.4 – 0.6
MBS Impact Modifier	5.0 – 10.0
Toner	As Required

  

<b>Clear Calendered Sheet</b>	<b>Use Level (phr)</b>
PVC Resin (K-60)	100.0
Thermolite 108	0.6 – 1.2
Internal Lubricants	1.2 – 1.5
External Lubricants	0.1 – 0.5
Acrylic Process Aid	1.5 – 2.0
Acrylic Process Aid (Metal Release)	0.7 – 1.0
MBS Impact Modifier	6.0 – 12.0
Toner	As Required

## Standard Packaging

Thermolite 108 heat stabilizer is available in pails, drums and totes.

## Safety and Handling

Thermolite 137 stabilizer may be handled with the same normal precautions as other butyltin mercaptide stabilizers and organic liquids. In case of contact with skin, thoroughly wash with soap and water. In case of contact with eyes, flush with water and get medical attention immediately. Use with adequate ventilation and avoid excessive or prolonged exposure to the vapors.

Indoor storage is recommended. Iron or non-stainless steel should be avoided for piping, valves, and pumps. Teflon® gaskets are recommended. No part of the stabilizer handling system wetted by liquid should contain copper.



### In US

PMC Organometallic, Inc.  
The PMC Group Building  
1288 Route 73, Suite 401  
Mount Laurel, NJ 08054

Customer Service  
1.855.638.2549  
(1.855.METALIX)  
Fax 1.856.638.2157

### In Europe

PMC Vlissingen B.V.  
C/o PMC OUVRIE  
44 rue Albert Einstein  
62220 CARVIN  
FRANCE

Customer Service  
33(0)3.91.83.71.56  
Fax 33(0)3.91.83.71.92

The information contained herein is correct to the best of our knowledge. Your attention is directed to the pertinent Material Safety Data Sheets for the products mentioned herein. All sales are subject to PMC Organometallic Inc.'s standard terms and conditions of sale, copies of which are available upon request and which are part of PMC Organometallic Inc.'s invoices and/or order acknowledgements. Except as expressly provided in PMC Organometallic Inc.'s standard terms and conditions of sale, no warranty, expressed or implied, including warranties of merchantability or fitness for a particular purpose, is made with respect to the products described herein. Nothing contained herein shall constitute permission or recommendation to practice any invention covered by a patent without a license from the owner of the patent.

## Environmental and Safety Information

BEFORE HANDLING THIS MATERIAL, READ AND UNDERSTAND THE MSDS (MATERIAL SAFETY DATA SHEET) FOR ADDITIONAL INFORMATION ON PERSONAL PROTECTIVE EQUIPMENT AND FOR SAFETY, HEALTH AND ENVIRONMENTAL INFORMATION. For Environmental, Safety & Toxicology information, contact our Customer Service Department at 1-855-638-2549 (1-855-METALIX) to request a Material Safety Data Sheet.

## More Technical Information Available

Ask your PMC Organometallix account manager for further information about other high quality PMC Organometallix's additives for use in PVC resins, PVC alloys and other polymer systems. PMC Organometallix produces a full line of heat stabilizers. In addition, PMC Organometallix's Technical Service staff is available to assist compounders and processors to solve formulation and processing problems.

## Thermolite® and ADVASTAB™ Heat Stabilizers

Thermolite® and ADVASTAB™ heat stabilizers are designed for use in the production of rigid, semi-rigid, foamed and flexible PVC products. PMC Organometallix has developed PVC heat stabilizers specifically for extruded siding, profiles and pipe, injection molding, blow molded bottles and calendered or extruded sheet. PMC Organometallix offers a full line of stabilizers that meet FDA requirements for food grade PVC packaging and a full line of NSF authorized stabilizers for PVC potable water pipe & fittings.

## ADVAPAK™, ADVALUBE™ and ADVAWAX™ for Rigid PVC Lubrication

Organometallix offers a wide range of performance lubricants for PVC processing. ADVALUBE™ and ADVAWAX™ include every lubricant class from esters to amides to paraffin waxes. ADVAPAK™ lubricants are custom formulations to meet specific customer requirements. ADVALUBE™, ADVAWAX™ and ADVAPAK™ products find uses in PVC pipe, siding, window profiles, film and sheet, molding, fencing, decking and trim applications.

## Biogenix Lubricants

PMC Biogenix's lubricants include Calcium, Zinc, Lithium, and Magnesium stearates that meet FDA requirements for food grade PVC packaging as well as NSF requirements for PVC potable water pipes & fittings. Our PVC lubricants such as Industrene®, Hystrene®, Kemester®, Kemamide® and heat stabilizers together offer a comprehensive PVC package for production of rigid, semi-rigid, foamed, and flexible PVC applications such as extrusion molding, injection molding, blow molding, calendering, siding, profiling, piping etc.

## CrystalWax for Rigid PVC Lubrication

Crystal manufactures a broad range of standard blends utilizing paraffin and polyethylene waxes along with the option of blending EBS, GMS and other lubricating esters produced by PMC Biogenix. CrystalWax lubricants are also available in custom formulations to meet specific customer requirements. CrystalWax formulations find uses in PVC siding, window profiles, fencing, decking and trim applications to highlight a few.



### In US

PMC Organometallix, Inc.  
The PMC Group Building  
1288 Route 73, Suite 401  
Mount Laurel, NJ 08054

Customer Service  
1.855.638.2549  
(1.855.METALIX)  
Fax 1.856.638.2157

### In Europe

PMC Vlissingen B.V.  
C/o PMC OUVRIE  
44 rue Albert Einstein  
62220 CARVIN  
FRANCE

Customer Service  
33(0)3.91.83.71.56  
Fax 33(0)3.91.83.71.92

The information contained herein is correct to the best of our knowledge. Your attention is directed to the pertinent Material Safety Data Sheets for the products mentioned herein. All sales are subject to PMC Organometallix Inc.'s standard terms and conditions of sale, copies of which are available upon request and which are part of PMC Organometallix Inc.'s invoices and/or order acknowledgements. Except as expressly provided in PMC Organometallix Inc.'s standard terms and conditions of sale, no warranty, expressed or implied, including warranties of merchantability or fitness for a particular purpose, is made with respect to the products described herein. Nothing contained herein shall constitute permission or recommendation to practice any invention covered by a patent without a license from the owner of the patent.