

Product Selection Guide^a

TYPE	GRADE	POWDER VERSION	DROP POINT (C°)	DENSITY (g/cm ³)	VISCOSITY			MELT INDEX @ 190°C (g/10min)	ACID NUMBER (mg-KOH/g)	ASPHALT	CARPET	MASTERSBATCH	COMPOUND	EMULSIONS	HMA	INKS & COATINGS	PVC LUBE	WAX MODIFICATION
					125°C (cP)	140°C (cP)	190°C (cP)											
C-Types: Coating Grades	C-10		103	0.906	18,600	16,650	3,550	2,250	-									
	C-12		118	0.907	212,000	125,000	31,400	400	-									
	C-13	•	137	0.913	-	-	-	190	-									
	C-15		101	0.906	8,950	6,100	1,800	4,200	-									
	C-16	•	103	0.908	16,650	10,000	2,850	1,700	2									
	C-17		>133	0.917	-	-	-	19	-									
	C-18		101	0.905	7,750	5,000	1,550	4,200	2									
N-Types: Non-Emulsifiable Grades	C-23	•	108	0.909	-	785,000	180,000	80	-									
	C-24			0.912	-	-	-	58	-									
	C-26		133	0.917	-	-	-	8	8									
	C-29		105	0.915	700	-	-	-	4									
	N-10	•	110	0.925	1,500	1,100	-	-	-									
	N-11	•	111	0.921	350	250	-	-	-									
	N-14	•	108	0.920	150	100	-	-	-									
E-Types: Emulsifiable Grades	N-15	•	164	0.902	- ^d	- ^d	700	-	-									
	N-21	•	121	0.950	600	400	-	-	-									
	N-30		110	0.924	1,050	700	-	-	-									
	N-34	•	104	0.910	450	300	-	-	-									
	N-35		104	0.913	700	-	-	-	-									
	E-10		105	0.942	800	525	-	-	17									
	E-14	•	104	0.939	375	260	-	-	17									
E-Types: Emulsifiable PP Grades	E-14E		104	0.939	225	160	-	-	17									
	E-16		105	0.943	700	500	-	-	17									
	E-20	•	112	0.960	1,500	900	-	-	17									
EE-2		112	0.960	1,500	900	-	-	17										
E-43	•	160	0.934	- ^d	- ^d	300	-	45										

■ Suggested^b

■ Applicable^c

a. This document is intended to be used as general guidance for product usage. It does not guarantee a Suggested or Applicable grade will work in your specific application. Please work with our technical team to determine a product solution that meets your needs.

b. "Suggested" indicates that the grade is commonly used in the respective application.
 c. "Applicable" indicates that the grade can generally be used in the respective application.
 d. Solid at this temperature