



Element14* PDMS 500

Element14* PDMS 500

INCI Name

Dimethicone

Product Description

Element14 PDMS medium viscosity oils are linear polydimethylsiloxane polymers with kinematic viscosities of 50, 100, 200, 350, 500 and 1,000 cSt.

Key Features and Typical Benefits

Silicones differ from organic compounds in both their physical and chemical properties.

- high and low temperature stability
- oxidative stability
- chemically inert
- low flammability
- low surface tension
- shear stability
- high compressibility
- low vapor pressure
- low odor
- soft, smooth silky feel
- non-oily feel
- spreadability
- low coefficient of friction
- lubricious

Typical Properties

	Element14 PDMS 50	Element14 PDMS 100	Element14 PDMS 200	Element14 PDMS 350	Element14 PDMS 500	Element14 PDMS 1000
Viscosity cSt	50	100	200	350	500	1000
Appearance	Clear, Colorless Liquid					
Specific Gravity at 25°C	0.96	0.97	0.97	0.97	0.97	0.97
Refractive Index at 25°C	1.4	1.4	1.4	1.4	1.4	1.4
Flash Point, Open Cup, °C	>300	>302	>302	>302	>302	>302
Pour Point, °C	-54	-47	-47	-47	-47	-47
Surface Tension Dynes/cm at 25°C	20.8	20.9	21	21.1	21.1	21.3

Potential Applications

Element14 PDMS medium viscosity oils may be considered for use in several industrial and consumer applications.

- heat and mechanical transfer fluid
- hydraulic fluid electrical insulating fluid
- water repellent
- polish ingredient
- mold release agent
- lubricant
- anti-foam
- personal care ingredient
- textile spin finishes
- paints and coatings additive

Patent Status

Nothing contained herein shall be construed to imply the nonexistence of any relevant patents or to constitute a permission, inducement or recommendation to practice any invention covered by any patent, without authority from the owner of the patent.

Product Safety, Handling and Storage

Customers should review the latest Material Safety Data Sheet (MSDS) and label for product safety information, safe handling instructions, personal protective equipment if necessary, and any special storage conditions required for safety. MSDS are available at www.momentive.com or, upon request, from any Momentive Performance Materials (MPM) representative. **For product storage and handling procedures to maintain the product quality within our stated specifications, please review Certificates of Analysis, which are available in the Order Center.** Use of other materials in conjunction with MPM products (for example, primers) may require additional precautions. Please review and follow the safety information provided by the manufacturer of such other materials.

Limitations

Customers must evaluate Momentive Performance Materials products and make their own determination as to fitness of use in their particular applications.

Contact Information

For product prices, availability, or order placement, contact our customer service by visiting momentive.com/ContactSilicones.

For literature and technical assistance, visit our website at: www.momentive.com

DISCLAIMER

The information provided herein was believed by Momentive Performance Materials Inc. (collectively with its subsidiaries, "Momentive") to be accurate at the time of preparation or prepared from sources believed to be reliable, but it is the responsibility of the user to investigate and understand other pertinent sources of information, to comply with all laws and procedures applicable to the safe handling and use of the product, and to determine the suitability of the product for user's intended application or use. All products supplied by Momentive are subject to Momentive's standard terms and conditions of sale. **MOMENTIVE MAKES NO WARRANTY, EXPRESS OR IMPLIED, CONCERNING THE PRODUCT OR THE MERCHANTABILITY OR FITNESS THEREOF FOR ANY PURPOSE OR CONCERNING THE ACCURACY OF ANY INFORMATION PROVIDED BY MOMENTIVE**, except that the product shall conform to Momentive's specifications. Nothing contained herein constitutes an offer for the sale of any product.

*Element14 is a trademark of Momentive Performance Materials Inc.

Momentive and the Momentive logo are trademarks of Momentive Performance Materials Inc.