

Keltan[®] 4450S

Product Description

Amorphous ethylene-propylene rubber with medium ENB (ethylidene norbornene) content and a medium Mooney viscosity.

The polymer structure of this product is characterized by a broader molecular weight distribution in combination with a higher level of Controlled Long Chain Branching compared to the Keltan[®] 4450. The structure ensures superior mixing and milling behavior, fast filler incorporation and high extrusion speeds.

Typical applications for this product are automotive solid profiles and molded goods.

Supply Form

Standard bales.

Raw Material Properties

Property	Nominal Value	Unit	Test Method
Mooney Viscosity ML (1+4) 125°C	42	MU	ISO 289
Ethylene content	52	wt %	ASTM D 3900A
ENB content	4.3	wt %	ASTM D 6047
Molecular weight distribution	CLCB		LANXESS

Other Product Features

Property	Typical Value	
Specific gravity	0.86	kg/dm ³
Stabilizer	non-staining	
Packaging	Wood & cardboard box; LDPE bale wrap; 40 standard bales (1000 kg).	

Keltan[®] 4450S

Storage Life/Conditions	The product should be stored dry and at temperature < 30 °C. Exposure to light has to be avoided.
Shelf life	36 months from date of production stored at above mentioned conditions.
Product Safety	Relevant safety data and references as well as the possibly necessary warning labels are to be found in the safety data sheet.

These raw material properties are typical and, unless specifically indicated otherwise, are not to be considered as delivery specification.

KELTAN[®] is a Registered Trademark of LANXESS Deutschland GmbH

This information and our technical advice - whether verbal, in writing or by way of trials - are given in good faith but without warranty, and this also applies where proprietary rights of third parties are involved. Our advice does not release you from the obligation to check its validity and to test our products as to their suitability for the intended processes and uses. The application, use and processing of our products and the products manufactured by you on the basis of our technical advice are beyond our control and, therefore, entirely your own responsibility. Our products are sold in accordance with the current version of our General Conditions of Sale and Delivery.

Issue number: LXS 11 / Date of issue: November 05, 2015 / Previous issue from March 30, 2015 / Information current as of date of issue. Please contact your ARLANXEO representative to determine if this publication has been revised.