



NATROCHEM, INC.
P.O. BOX 1205
SAVANNAH, GA 31402
(912) 236-4464 FAX: (912) 236-1919
www.natrochem.com

DATA SHEET R153 DLC®-68

R153 DLC-68 is a polybutadiene, calcium silicate blend used as a coagent for EPDM and EPM. When incorporated into peroxide cure systems, this product functions as a non-extractable process aid, and low temperature tackifier. At higher loadings, it gives improved heat, chemical and oil resistance and increases tensile strength in sulfur cure formulations.

TEST	TEST METHOD	SPECIFICATION
Actives Content, %	QCL-8.2.4-2-1	66 - 70
Carrier Content, %	QCL-8.2.4-2-1	30 - 34

TYPICAL PROPERTIES

Actives Content, %	68
Carrier Content, %	32
Specific Gravity (Apparent)	1.16
Packaging	50# Net, Multi-wall Bags
Color	Off-White

Date of Revision: 6/17/11

The information in this data sheet is derived from the best available sources and is believed to be accurate. However, no guarantee is expressed or implied regarding the accuracy of these data or the use of this product, nor are any statements in this bulletin intended as recommendations to use our products in the infringement of any patents.

OTHER NATROCHEM PRODUCTS

**DLC® - Galex® - Rosin Oils - Rosin Pitches - Tarene™
Natro-Flex™ - Tar-Cel® - Natro-Cel®**